

LF 8600 Series

PRODUCT DESCRIPTION

Budget monomeric calendered self-adhesive laminating film

Face material:

LF 8600 CG : 80µm clear gloss PVC

LF 8600 CM : 80µm clear matt PVC

Adhesive:

Solvent acrylic permanent transparent

Liner:

PET 65 gsm

TYPICAL USE

Laminating films specifically designed for the JT8600 Series for short-term indoor and outdoor applications on flat surfaces in order to:

- retard colour fade and protect printing media against UV radiation and abrasion
- enhance colours of the prints
- customize the media with homogeneous matt and glossy finishes

PROCESSING

Compatible with solvent, eco-solvent and Latex inks. End user to determine the suitability of the product on UV inks.

LF 8600 Series needs to be laminated on JT 8600 Series to achieve optimal protection and durability.

For specific settings of the laminator, please consult the technical manual that comes with the laminator from the original supplier. The printed media should be perfectly dry prior to lamination and solvent print should be left to dry for at least 24h.

Mactac Laminating media must be applied following the instructions in TB 4.1 "Guidelines on handling, converting and applying Mactac Digital media".

SHELF LIFE

1 year when stored at 20 to 25°C and 55± 5 % relative humidity (in the original packaging).

CHEMICAL RESISTANCE

Not suitable for use in contact with ketones, esters, aromatic and chlorinated hydrocarbons as for contact with water or detergents, alcohol and other aliphatic solvents.

PHYSICAL PROPERTIES (TYPICAL VALUES)

Adhesive data, 25°C (N/25 mm)	Average values	Test method
Quick tack on SS	5.0	FTM 9
Peel 24 hours on SS	12.0	FTM 1

Dimensional stability

Application Shrinkage	Max. 0.8 mm	FTM 14
-----------------------	-------------	--------

Temperature ranges

Minimum application temperature	+ 10°C
Service temperature range of use	- 20°C to + 70°C

Certification

Fire certification	Self-extinguishing	Mactac test
--------------------	--------------------	-------------

EXPECTED DURABILITY*

Asia Pacific Zone 2

Unprocessed	3.0 years	ISO 4892-2.
Laminated	2.0 years	ISO 4892-2.

*For more information, refer to Technical Bulletin 7.5: "Outdoor Durability of combined MACTac print media and laminates".

Note : Overlamination of the inkjet-printed material delays the eventual colour fading that may occur over time. This colour fading is dependent on the quality of the inkjet inks, the orientation of the printed material, the angle of display and the exact geographical location of exposure.

Exposure to severe temperatures, ultraviolet light, and/or conditions in Southern European countries, tropical, sub-tropical or desert regions will cause more rapid deterioration. This also applies to polluted areas, high altitudes and south-facing exposure. No durability warranty is given for horizontal exposure.

DISCLAIMER

All Mactac statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Mactac products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purposes. All Mactac's products are sold subject to Mactac's general terms and conditions of sale.